



Product information

Product full identity:

Unplasticised Polyvinyl Chloride

U-PVC is rated self-extinguishing, has excellent chemical resistance with high mechanical and tensile strength, together with a high degree of stability. U-PVC is easily weldable but has a limited operating temperature range of 0°C to +60°C.

Properties

- » Machines well to a polished finish
- » Solvent Cemented & Welded
- » Relatively less expensive than other plastics
- » Strong and stiff
- » Flame retardant grades available
- » Chemical resistant
- » Self extinguishing
- » UV stabilised grades available
- » Drinking water approved
- » Food compliant grades available

Applications

- » Corrosive fluid handling
- » Valves
- » Tanks
- » Water applications
- » Air conditioning & ventilation systems
- » Threaded bolts

This document contains

- » Technical Datasheet (Page 2)
- » Chemical Datasheet (Page 3)
- » Safety Datasheet (Pages 4-5)

For any further information regarding food, fire and water certificates then please contact the sales team on 01604 700 880

Technical Properties

Physical Properties	Test	Unit	Result
1. Specific gravity	ISO 1183	g/cm ³	1.45
2. Water absorption	ISO 62	%	<0.2
3. Maximum service temp. Upper temp limit (no stronger mechanical stress involved)	-	°C	60
Lower temp limit	-	°C	-15
Mechanical Properties	Test	Unit	Result
1. Tensile strength at yield	ISO 527	MPa	-
2. Elongation at yield	ISO 527	%	3
3. Tensile strength at break	ISO 527	MPa	30
4. Elongation at break	ISO 527	%	>10
5. Impact strength	ISO 179	kJ/m ²	no break
6. Notch impact strength	ISO 179	kJ/m ²	3
7. Ball indentation / Rockwell hardness	ISO 2039-1	MPa	-
8. Shore-D	ISO 53505	-	80-82
9. Flexural strength	ISO 178	MPa	90
10. Modulus of elasticity	ISO 527	MPa	-
Thermal Properties	Test Method	Unit	Result
1. Vicat-softening point VST/B/50	ISO 306	°C	75
2. Heat deflection temperature HDT/B	ISO 75	°C	-
HDT/A	-	°C	-
3. Coefficient of linear thermal expansion	ASTMD 696	µm/ (m * °K)	80
4. Thermal conductivity at 20 °C	DIN 52612	W / (m*K)	0.14
Electrical Properties	Test Method	Unit	Result
1. Volume resistivity	IEC 6093	Ω x m	>10 ¹⁵
2. Surface resistivity	IEC 6094	Ω	>10 ¹³
3. Dielectric constant at 1MHz	IEC 60250	abs	3
4. Dielectric loss factor at 1 MHz	IEC 60250	tan	0.01
5. Dielectric strength	IEC 60243	kV/mm	20-40
6. Tracking resistance	IEC 60112	-	-
Additional Data	Test Method	Unit	Result
1. Bondability	-	-	+
2. Food compliance	FDA	-	+
3. Flammability	UL 94	-	V-0

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

Key:

Yes	Limited	No data
+	0	-

Chemical Properties

Agent	Conc %	Working Temp		Agent	Conc %	Working	Temp
		20°C	60°C				
Acetic Acid	100	+	-	Hydrofluoric acid	40	+	o
Acetone	100	-	-	Hydrogen peroxide	10	+	+
Ammonia	Conc.	+	o	Hydrogen Sulphide		+	+
Ammonium chloride		+	+	Isopropyl Alcohol	100	+	+
Amyl Alcohol		+	o	Mercurochrome		o	-
Benzene		-	-	Methyl alcohol	100	+	+/o
Bleaching Solution	12,5 Cl	+	-	Methyl ethyl ketone	100	-	-
Boric Acid	100	+	o	Methylene chloride	100	-	-
Brake Fluid		+	+	Nitric acid	50	+	+
Butyl Acetate		-	-	Nitrobenzine		-	+
Calcium Chloride		+	+	Oxalic Acid		+	+
Carbon disulphide	100	-	-	Ozone, gas	ca. 0,5 ppm	+	+
Carbon Tetrachloride		-	-	Paraffin Oil	100	+	o
Chlorine, gas	100	o	-	Perchlroethylene		-	-
Chlorobenzene	100	-	-	Petroleum	100	+	+
Chloroform		-	-	Petroleum, aromatic free	100	+	+
Citric Acid	10	+	-	Phenol, aqu	ca.9	o	-
Cresol		-	-	Phosphoric Acid	50	+	+
Cyclohexanone	100	-	-	Potassium hydroxide liquor	50	+	+
Cyclohexene	100	+	o	Propyl alcohol		+	o
Diesel Fuel		+	o	Pyridine		-	-
Diethylene oxide, THF		-	-	Silicone oil		+	+
Ethyl acetate	100	-	-	Sodium carbonate. aqu		+	+
Ethyl alcohol	96	+	o	Sodium chloride, aqu		+	+
Ethylene Chloride	100	-	-	Sodium Hydroxide liquor	15	o	o
Formic Acid	10	+	o	Sodium Hydroxide liquor	60	o	o
Frost protection agent	Petrol	+	+	Sodium hydrogen sulphite		+	+
Fuel, aromatic free		+	+	Sodium nitrate, aqu		+	+
Glycerine	100	+	+	Sodium thiosulfate		+	+
Glycol	100	+	+	Sulphuric Acid	96	+	+/o
Heating oil		+	+	Tetrahydrofurance	100	-	-
Heptane	100	+	+	Toluene	100	-	-
Hydrochloric acid	conc.	+	+	Trichlorethylene	100	-	-
				Xylene		-	-

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

Key:

Yes	Limited	No data
+	o	-

Safety Properties

Substance / preparation and company detail

Polyvinylchloride
ABG Plastics
10 Sketty Close,
Brackmills,
Northampton,
NN4 7PL
01604 700 880

Composition / indications to components

Chemical characteristics: polymer of vinyl chloride
CAS-number: not necessary

Possible dangers

Unknown

First-aid measures

General comment: medical aid is not necessary
First-aid measures: none
Routes of exposure: none
Symptoms / effects: none

First-fighting measures

In case of fire please use gas mask and breathing equipment in depending of circulating air. Fire residues must be disposed of according to the local instructions. Suitable fire-fighting appliance: water fog, foam, fire fighting powder, carbon dioxide
Hazard warning notice: not applicable

Measures in case of unintended release

Person-related measures: none
Environmental protection measures: not applicable
Cleaning equipment: not applicable
Unsuitable cleaning products: not applicable

Handing and storage

Handling: no special regulations must be observed
Storage: unlimited good storage property

Limitation of exposition

Special design of techn. processing facilities: not required
Tolerance levels: none
Exposure measurement procedures: none
Respiratory protection: not required
Eye protection: not required
Body protection: not required

Physical and chemical characteristics

Phenotype

Phenotype / form: semi-finished product, solid state
Colour: dark grey
Smell: not applicable

Change of state

Flash point: not applicable

Other remarks

Density: 1.44 g/cm³

Safety Properties

Stability and reactivity

Thermal decomposition: above appr. 200°C

Dangerous decomposition products:

Besides hydrochloric acid also carbon dioxide and water will develop during the burning process. In case of incomplete burning also carbon monoxide and traces of phosgene may arise.

Use of stabilisers: none

Exothermic reactions: none

Notices regarding state of aggregation: none

Conditions to be avoided: none

Substances/media to be avoided: none

Toxic information

During several years of usage no effects being harmful for the health were observed.

Ecological information

No biodegradation, no solubility in water, no effects being harmful to the environment must be expected.

Mobility: not applicable

Accumulation: not applicable

Eco-toxicity: not applicable

Waste-disposal information

Can be recycled or can be disposed of together with household rubbish (acc. To local regulations).

Waste key for the unused product: EAK-Code 120 105

Waste name: waste of polyvinylchloride

Transport information

No dangerous product in respect to / according to transport regulations

Notice/symbol transport containers: none

Special marking for containers: none

Regulations

Marking according to GefStoffV/EG: no obligation for marking

Water danger class: class 0 (self classification)

Domestic requirements to be observed: none

Further information

The information is based on our current knowledge. They are meant to describe our products in respect to safety requirements. They do not represent any guarantee of the described product in the sense of the legal guarantee regulations.